

Pacific TPU 300 series low melting point hotmelt TPU

300 series can be used for sealing tapes, hotmelt adhesive tapes, heat transfer lamination, fabric lamination and auto industry.

Item	Appearance	Hardness (Shore A)	Specific Gravity (g/cm ³)	Flowing Temp. (°C)	MFI (g/10min 150°C*2.16kg)	Tack Free Time (min)
3150	White	97±3	1.20±0.02	60~80	10±5	6
3151	White	97±3	1.20±0.02	65~85	15±5	5
3152	White	97±3	1.20±0.02	65~75	20±5	6
3153	White	97±3	1.20±0.02	50~60	5±3	6
3154	White	97±3	1.20±0.02	65~70	10±5	20

