

Pacific TPU 400 series high melting point hotmelt TPU

Good flexibility, excellent abrasion resistance, good elasticity, stickiness, eco-friendly.

Item	Appearance	Hardness (Shore A)	Specific Gravity (g/cm ³)	Flowing Temp. (°C)	MFI (g/10min 150°C*2.16kg)	Tack Free Time (min)
4160	Clear	75±3	1.19±0.02	90	20±5	15
4117	Clear	80±3	1.20±0.02	110	4±2	8
4190	Clear	80±3	1.20±0.02	110	3±1	6
4130	Clear	85±3	1.20±0.02	105	10±5	9
4131	Clear	85±3	1.20±0.02	110	15±5	9
4132	Clear	85±3	1.20±0.02	110	20±5	9
4133	Clear	85±3	1.20±0.02	115	5±3	7
4180	Clear	80±3	1.20±0.02	100	35±10	8

