

TECHNICAL DATA SHEET

UREPAC[®] RIGID 18 28

PRODUCT DESCRIPTION

UrePac[®] Rigid 18 28 is a two component, polyurethane rigid foam comprising of a polyether polyol and MDI based isocyanate. The system has been developed for fast curing and excellent insulation performance for general purpose machine dispense applications.

PRODUCT FEATURES

- Exceptional Insulation
- Fast demould
- 1: v/v mix ratio

UREPAC RIGID 18 28 POLYOL SPECIFICATION


Appearance:	Clear Pale Straw liquid
Specific Gravity (22°C):	1.08 ± 0.02 g/mL
Viscosity (Brookfield) (22°C):	400 ± 200 mPa.s

Spindle 1 Speed 50

UREPAC ISO2001 MDI ISOCYANATE SPECIFICATION

Appearance:	Clear brown liquid
Specific Gravity (22°C):	1.23 ± 0.02 g/mL
Viscosity (Brookfield) (22°C):	210 ± 70 mPa.s

Spindle 1 Speed 50



MIXED SYSTEM SPECIFICATION

Mix Ratio:	By Weight	100 Polyol : 110 Isocyanate
	By Volume	100 Polyol : 100 Isocyanate


Test	Specification	Units
Cream Time (22°C): <i>Time from when mixing commences till the liquid starts to expand.</i>	18 ± 2	seconds
String time (22°C): <i>Time from when mixing commences till "strings can be pulled from the surface of the rising foam.</i>	60 ± 5	seconds
Rise time (22°C): <i>Time from when mixing commences till the foam finishes expanding.</i>	85 ± 5	seconds
Typical Demould (40°C)	300	seconds
Free Rise Density (22°C):	28 ± 2	kg/m ³

(Obtained from Laboratory 63g cup test, results will vary depending on mix quantities)

TYPICAL CURED FOAM PROPERTIES

Test	Method	Specification
Moulded Core Density:	ASTM D1622	35 ± 2 kg/m ³
Dimensional Stability (90°C)	AS2489.6	<0.2%
(-20°C)	(@ 72 hours)	<0.2%
Closed Cell Content:	ASTM D6226	90-95%
Initial K Value:	ASTM C518	0.0200 W/mK
R Value (@ 50mm)	Insulation thickness in meters divided by the K value	2.5
Compressive Strength:	ASTM D1621	
Parallel		205 ± 10 kPa
Perpendicular		175 ± 10 kPa
Water Absorption	ASTM D8242	< 2%

After 7 days cure @ 22°C unless otherwise specified.



PACKAGING OPTIONS:

Packaging	UrePac Rigid 18 28 Polyol	UrePac ISO2001 MDI Isocyanate
205L Closed Head Drum	210kg	250kg
1000L IBC	1050kg	1250kg

STORAGE

POLYOL should be stored in closed containers under dry conditions out of direct sunlight between 18 and 25°C.

ISOCYANATE should be stored separately from the polyol component, but under the same conditions.

Both products will have a minimum shelf life of six months when stored under these conditions.

CURED PRODUCT: Like all polyurethanes based on aromatic isocyanates this foam is **not** UV colour stable and will have surface discolouration and degradation if exposed to UV radiation and sunlight. Please speak to our technical consultants regarding your options if this product is required for use in external applications.

PROCESSING CONDITIONS:

All processing conditions are given as a guide only, it is the responsibility of the customer to satisfy themselves that the product is suitable for their requirements by running closely monitored trials prior to production.

COMPONENT PREPARATION


POLYOL does not need to be mixed prior to use.

ISOCYANATE does not need to be mixed prior to use.

Both Components should be preconditioned to 22-25°C to ensure that the components will have consistent reactivity and performance. If processing in a machine this usually requires recirculation for at least an hour prior to production commencing.

MOULD TEMPERATURES

Mould temperatures should be conditioned to 35-45°C to ensure optimal skin definition and demould times for this product.



DISPOSAL

Liquid Systems: Liquid polyol or isocyanates should be disposed of with an EPA approved industrial waste company which meet all applicable federal, state and local laws and regulations.

Cured Urethanes: Fully reacted and cured polyurethanes are inert and can be disposed of as regular landfill.

Container: Dispose of decontaminated drums in accordance with all applicable federal, state and local laws and regulations.

Do Not Re-use Empty Container.

Do Not Cut or Weld Empty Container.

WATER CONTAMINATION CAN CAUSES DANGEROUS PRESSURE BUILD UP IN ISOCYANATE DRUMS

DISCLAIMER

This information is given in good faith but without warranty and is supplied to users based on our general experience and, where applicable, on the results of tests on samples of typical manufacture. However, because of the many factors which are outside our knowledge and control that can affect the use of these products, it is imperative that the end user is satisfied that the material will meet their individual processing and performance requirements. Pacific Urethanes Pty Ltd cannot accept liability for any injury, loss or damage resulting from reliance upon this information.

All sales of this product shall be subject to Pacific Urethanes' Terms and Conditions of Sale. For a copy of these terms please contact us at info@pacificurethanes.com.

For additional information, consult the Safety Data Sheet (SDS) for this product.

Revision Number: 01

Revision Date: 25/04/2019

